

SPECIFICATION

Electronic Version 1.2.8

Stylesheet Version 1.0

[METHOD FOR FABRICATING NITRIDE READ-ONLY MEMORY]

Background of Invention

[0001] Field of Invention

[0002] The present invention relates to a method for fabricating a read-only memory (ROM). More particularly, the present invention relates to a method for fabricating a nitride read-only memory.

[0003] Description of Related Art

[0004] A method for fabricating a nitride read-only memory in the prior art is described as follows. An oxide/nitride/oxide (ONO) stacked charge-trapping layer is formed on a substrate, and then patterned into a plurality of ONO strips. An ion implantation is performed to form doped regions in the exposed substrate serving as buried bit lines. An isolating oxide layer is formed on each doped region, and then a plurality of polysilicon word lines are formed on the substrate crossing over the ONO strips.

[0005] In the prior art, the ONO stacked layer is patterned with a patterned photoresist layer as an etching mask. However, as shown in FIG. 1, when the bottom oxide layer of the ONO stacked layer 108 is being etched, the top oxide layer 106 is etched simultaneously to cause corner loss or even corner indents. Therefore, the electrical properties around the edges of the ONO stacked layer 108 are changed, which may result in severe problems.

[0006] To prevent the problems caused by corner loss or corner indents, a method is provided in the prior art that increases the thickness of the top oxide layer to reduce the degree of the influence of corner loss or corner indents. However, an increased thickness of the top oxide layer does not meet the requirements for device

miniaturization.

Summary of Invention

[0007] Accordingly, this invention provides a method for fabricating a nitride read-only memory to prevent over-etching of the top oxide layer, so as to reduce corner loss of the ONO stacked layer. It is thereby possible to prevent the electrical properties of the device from being deteriorated, as well as to meet the requirements for device miniaturization because the thickness of the top oxide layer needs not to be increased.

[0008] A method for fabricating a nitride read-only memory of this invention comprises the following steps. An ONO stacked layer and a protective layer are sequentially formed on a substrate, wherein the protective layer comprises a material different from silicon oxide, such as silicon nitride. An etching process is performed to pattern the protective layer and the ONO stacked layer to expose a portion of the substrate, wherein the etching rate of the protective layer is lower than that of the top oxide layer. Thereafter, the protective layer is removed by using wet etching. An ion implantation is performed to form buried bit lines in the exposed substrate, and then an insulator is formed on each buried bit line. A plurality of word lines are formed on the substrate crossing over the buried bit lines.

[0009] In another method for fabricating a nitride read-only memory of this invention, the protective layer on the ONO stacked layer is not removed after the ONO stacked layer are patterned. The protective layer comprises a material different from silicon oxide, such as silicon nitride, and has a thickness smaller than 50 Å, for example.

[0010] Since the protective layer having a lower etching rate is formed on the ONO stacked layer to protect the top oxide layer, corner loss of the top oxide layer can be reduced and the electrical properties of the device are not deteriorated.

[0011] It is to be understood that both the foregoing general description and the following detailed description are exemplary, and are intended to provide further explanation of the invention as claimed.

Brief Description of Drawings

[0014] FIG 2A~2E schematically illustrate a process flow of fabricating a nitride read-only memory according to a preferred embodiment of this invention.

[0015] FIG 2A~2E schematically illustrate a process flow of fabricating a nitride read-only memory according to the preferred embodiment of this invention.

[0017] Refer to FIG. 2B, a protective layer 210 is formed on the ONO stacked layer 208. The protective layer 210 comprises a material different from silicon oxide, such as silicon nitride, and has a thickness smaller than 50 Å.

[0019] Refer to FIG. 2D, the protective layer 210 is removed by using wet etching. An ion implantation is then conducted to form buried bit lines 212 in the substrate 200 exposed by the patterned ONO stacked layer 208. However, the wet etching process can be omitted optionally to leave the protective layer 210 on the ONO stacked layer

[0021] Since the protective layer having a lower etching rate is formed on the ONO stacked layer to protect the top oxide layer, corner loss of the top oxide layer can be reduced and the electrical properties of the device are not deteriorated. Meanwhile, there is no need to increase the thickness of the top oxide layer, so device miniaturization will not be restricted.

[0022] It will be apparent to those skilled in the art that various modifications and variations can be made to the structure of the present invention without departing from the scope or spirit of the invention. In view of the foregoing, it is intended that the present invention covers modifications and variations of this invention provided they fall within the scope of the following claims and their equivalents.